

Types available

Thickness (mm)	30	50	50	100	150	200	250	300
Width (mm)	200	300						
Length (mm)	150			300 & 600				
Packing (piece)	120	48	24	12	8	6	4	

Coating Material

Thickness (mm)	ITM-FIBERMAX® Coat SL	ITM-FIBERMAX® Coat S
Maximum Use Temperature (°C)	1500	1500
Bulk Density (kg/m³) WET	1300	1400
Bulk Density (kg/m³) DRY	800	1600
Installation Method	Spray	Spray
Coverage (kg/m²)	5	2~3
Standard Packing (kg)	20	25

Cement

	ITM-FIBERMAX® Cement
Maximum Use Temperature (°C)	1400
Adhesion at Room Temperature (Pa)	800~1000
Setting Property	Air Setting
Coverage (kg/m²)	8~10
Standard Packing (kg)	20



All grades are also available in high purity grades. Na₂O (Sodium Oxide) and Fe₂O₃ (Ferrum Oxide) are drastically reduced for semiconductor and advanced industry.